

Material Properties	
Description	Value
Water sorption	30 µg/mm ³
Brookfield viscosity at 23°C	0.9 - 1.4 Pa's
Water solubility	5 µg/mm ³
Flexural Strength	85 Mpa
Flexural Modulus	2.100 Mpa
Hardness, Shore D	D 89-90