

Material Properties	
Description	Value
Tensile Strength	57 Mpa
Elongation at Break	3.60%
Heat Deflection Temperature	78°C at 1.82 MPa
Flexural Strength	129 Mpa
Flexural Modulus	3155 MPa
Hardness, Shore D	89
Specific Gravity	1.1 - 1.11 g/cm ³
Viscosity	760 cP at 25°C