

Material Properties	
Description	Value
Water sorption	32 µg/mm ³
Brookfield viscosity at 23°C	1.0 - 1.5 Pa•s
Water solubility	1.6 µg/mm ³
Flexural Strength	85 Mpa
Flexural Modulus	2.100 MPa
Hardness, Shore D	D 80 - 90
Residual monomer	1%