

Material Properties	
Description	Value
Tensile Strength	56 Mpa
Elongation at Break	3.50%
Flexural Strength	115 MPa
Flexural Modulus	3350 MPa
Heat Deflection Temperature	140°C (284°F)