

<b>Material Properties</b>	
<b>Description</b>	<b>Value</b>
Water sorption	27.8 $\mu\text{g}/\text{mm}^2$
Brookfield viscosity at 23°C	0.9 - 1.4 Pa's
Water solubility	1.4 $\mu\text{g}/\text{mm}^2$
Flexural Strength	80.9 Mpa
Flexural Modulus	2123 Mpa
Charpy impact strength, unnotched	13.3 kJ/m <sup>2</sup>
Elongation at break	3.81%