

<b>Material Properties</b>	
<b>Description</b>	<b>Value</b>
Tensile Strength	68-73 Mpa
Elongation at Break	6-7 %
Tensile Modulus	2950 - 3250 MPa
Flexural Strength	120 - 126 Mpa
Flexural Modulus	3340 - 3570 Mpa
Hardness, Shore D	87
Heat Deflection Temperature @ 1.82 Mpa	62.5°C
Impact Izod	30 J/m
Viscosity	460cP @ 30°C
Water Absorption	0.67% at 48 hours
Post-Processing For Results Above	UV SCU 2 X 60 min.