

<b>Material Properties</b>	
<b>Description</b>	<b>Value</b>
Temperature @ 5% Weight Loss	263°C
Ash Content (after 900°C)	0
Density	1.08 g/cm <sup>3</sup> @ 25°C
Viscosity	200 cP @ 30°C